## CUR 05



## **Curekind CBS(CZ)**

D E S C R I P T	N-cyclohexyl-2-benzothiazoleSulfenamide	Items	Specification	
			Powder	Granule
		Appearance	Grey-white Powder(Granule)	
		Initial Melting Point, min.	97.0	97.0
		Heat Loss,% max.	0.5	0.5
		Ash, %	0.4	0.4
 0	C <sub>13</sub> H <sub>16</sub> N <sub>2</sub> S <sub>2</sub> M.W. 264.4	Density, g/cm <sup>3</sup>	1.30	1.30
N	CAS No.: 95-33-0 EINECS No.202-411-2	Residue on 150µm,%max.	0.1	-
		Residue on 63µm,% max.	0.50	-

Characteristics Curekind<sup>®</sup> CBS is Grey-white Powder(Granule). Soluble in benzene and ethyl acetate, insoluble

in water, slight soluble in gasoline.

Application Curekind<sup>®</sup> CBS is a good delayed action accelerator, suitable for natural and synthetic rubber and tire etc rubber products, can improve the physical and mechanical properties of rubber products. CBS is regulated for use in articles in contact with food as specified under FDA 21 CFR177.2600 and under BgVV XXI, Category 4.

Safety and Toxic Refer to the MSDS

Storage Stone in closed containers in a cool, dry, well-ventilated place. Avoid exposure under direct sunlight.

Package Co-extruded paper bag lined with PE plastics film bag. N.W.25kg/bag; N.W.500kg/pallet.

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.

CUREKIND®CBS(CZ)

TECHNICAL DATA SHEET (TDS) version 1.3

## Ningbo Actmix Rubber Chemicals Co., Ltd.

TEL:+86-574-81880068 FAX:+86-574-88002102 Email: actmix@actmix.cn Http://www.actmix.cn