


Curekind ZBOP/S

D E S C R I P T I O N	 <p>(R = alkyl)</p> <p>zinc dialkyldithiophosphate</p>	Items	75% zinc dialkyldithiophosphate bounded 25%SiO ₂ - powder
		Appearance	White powder
		Sulfur, %	10.5-13.5
		Ash. %	43.0-46.0
		Density (25°C, g/cm ³)	1.20

Characteristics Curekind[®] ZBOP/S, a fast curing secondary accelerator for NR and EPDM.

Application Curekind[®]ZBOP/S mainly used as curing accelerator for EPDM, non-blooming, lower cost and fast curing rate. Because of non-amine based structure, Curekind[®]ZBOP/S can be used to Non-nitrosamine formed curing systems. Curekind[®]ZBOP/S is regulated for use in articles in contact with food as specified under BgVV.XXI, category 4, and is not regulated for use in FDA food contact applications.

Safety and Toxic Refer to the MSDS

Storage Store in closed containers in a cool, dry, well-ventilated place. Avoid exposure under direct sunlight.

Package Co-extruded paper bag lined with PE plastic film bag. N.W. 25kg/bag, N.W. 600kg / pallet.

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from references. Therefore it is not valid legally and does not signify any guarantee to customers of successful applications of the product according to their own formulas. However, our company will offer professional services in technology at utmost to facilitate customers to achieve expected purpose of product applications.